



Dulux TRADE

DULUX TRADE DIAMOND EGGSHELL

Issued November 2010

408

PRODUCT INFORMATION

Typical Use	Dulux Trade Diamond Eggshell is a tough, durable and attractive mid sheen finish. By using Diamond Technology from Dulux Trade it is 10 times more stain resistant than standard water-based eggshell finishes and 10 times tougher than vinyl silks. It is quick drying and of low odour compared to solvent-based paints, and therefore ideal for use where minimum disruption is important. Dulux Trade Diamond Eggshell can be used over surfaces previously decorated with solvent-based paints, providing proper surface preparation is carried out. Suitable for interior use on plaster, masonry and wood. Before preparing any surface for painting, read the Health, Safety & Environmental information on page 2 about old lead-based paints.
Codes according to the List of Wastes Regulations	Product as supplied: Assigned as non-hazardous waste code 08 01 12 waste paint and varnish other than those mentioned in 08 01 11. Part-used containers, containing dried residues of the supplied product: Assigned as non-hazardous waste code 08 01 12 waste paint and varnish other than those mentioned in 08 01 11 Used containers, rigorously scraped out and containing dried residues of the supplied product: Assigned as non-hazardous waste code 15 01 02 plastic packaging OR non-hazardous waste code 15 01 04 metal packaging. "Rigorously scraped out" means removing the maximum amount of product from the container by physical or mechanical means (draining or scraping) to leave a residue or contamination that cannot be removed by such means. These codes have been assigned based on the actual composition of the product both as supplied and as dried residues. If mixed with other wastes, the waste codes quoted may not be applicable.
Pack Size	1, 2.5 and 5 litre.
Colour Range	See appropriate Dulux Trade colour literature.
Film Properties	Chemical Resistance: Not recommended. Heat Resistance: Not recommended for use on heated surfaces eg radiators. Water Resistance: Resistant to the levels of atmospheric humidity present in normal interior environments and will withstand repeated washing. Suitable for use in kitchens and bathrooms. Not suitable for use on immersed surfaces or where there is heavy and prolonged condensation. Do not use externally.
Composition (nominal)	Pigment: Lightfast Non Lead Pigments. Binder: Acrylic Copolymer Emulsion. Solvent: Water.
Volume Solids	White 37% (nominal), other colours will vary.
Application Method	Brush, roller or spray.
Film Thickness	<i>Film thickness will be dependent on the coverage achieved.</i> Wet: 63 microns. Dry: 23 microns.
Drying Times	<i>Single coat at standard thickness:</i> Touch Dry: Dependent upon temperature and humidity. Recoat: 4-6 hours. The drying time will vary according to temperature and humidity e.g. the drying times quoted will be significantly longer in cold, damp conditions.
Practical Coverage	A guide to the practical coverage which can be achieved under normal conditions is up to 16m ² / litre.
Thinning	Sealing new or bare surfaces: Add up to 1 part clean water to 10 parts paint.

Normal use (not to be exceeded): Thinning is not usually required.

Conventional spray application: Add up to 1 part clean water to 5 parts paint.

Airless spray application: Thinning is not usually required.

Spray Recommendations Conventional Spray: Satisfactory through most equipment.

Airless Spray: A typical set up for airless spray application would be a minimum working pressure on paint of 133 bars (2000lb/sq in) with a spray tip size 0.38mm (15 thou) and a spray tip angle 65°.

Cleaning Up

After use, remove as much paint as possible from brushes before cleaning with clean water. Do not use or store in extremes of temperature and protect from frost.

SURFACE PREPARATION

Surfaces must be clean, dry, free from all defective or poorly adhering material, dirt, grease, wax etc. Thoroughly rub down previously painted surfaces, using 'wet flattening' methods where possible, then wipe off with a damp, lint free cloth.

Treat knots with a suitable knotting solution.

New or bare surfaces should be primed with an appropriate **Dulux Trade** primer.

Any surface defects should be filled with the appropriate **Polycell Trade Polyfilla**.

SYSTEM INFORMATION**Stir thoroughly before use.**

The normal finishing process is 2 full coats of **Dulux Trade** Diamond Eggshell, but on previously painted surfaces in good condition, where similar colours are used, 1 coat may be sufficient.

When applying water-based paints to surfaces previously decorated with a conventional solvent-based paint, very thorough surface preparation will be necessary.

As with other water-based paints, do not use when the temperature is below 10°C.

HEALTH, SAFETY & ENVIRONMENTAL INFORMATION**WATER-BASED PAINT**

Ensure good ventilation during application and drying.

Do not breathe spray. When spraying inside, wearing a cartridge mask of Assigned Protection Factor 40 x OEL for particulates is recommended.

Avoid contact with skin and eyes. When applying it is advisable to wear eye protection.

In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.

After contact with skin, wash immediately with plenty of soap and water or a proprietary skin cleanser. Do not use solvent, thinners or white spirit.

Keep out of the reach of children.

If swallowed, seek medical advice immediately and show this container or label.

Do not use or store by hanging on a hook. Do not empty into drains or watercourses.

Safety data sheet available for professional user on request.

Avoid the inhalation of dust. Wear a suitable face mask if dry sanding.

Special precautions should be taken during surface preparation of pre-1960s paint surfaces over wood and metal as they may contain harmful lead. For further advice contact ICI Paints Technical Group, at ICI Paints/AkzoNobel, Wexham Road, Slough SL2 5DS.

Tel: 08444 817 818

EU limit value for this product (cat A/a) : 75g/l (2007) / 30g/l (2010)

Pure Brilliant White - This product contains max. 20g/l

Tint bases – This product contains max. 22g/l

See www.duluxtrade.co.uk

VOC Content Low 0.30% - 7.99%. VOCs (Volatile Organic Compounds) contribute to atmospheric pollution.

Dulux Trade, The ICI Roundel, Polycell, Polyfilla, Diamond Technology and the distinctive livery are trademarks of AkzoNobel.

© AkzoNobel 2010 (05112010IT SDS408)

